



BULLNOSE BOARDS



CERTIFICATIONS



TSCA
Title VI



The mark of responsible forestry
*Upon request

BULLNOSE BOARDS

USE REFERENCE

- Shelving
- Stair treads
- Board

SUBSTRATE

MDF - MDP

FINISHES

- Raw
- Primed

FEATURES

- Blemish and defect free
- Superior finish
- SCS-certified materials
- Light weight
- Multiple countries
- TSCA certified
- Machines well
- Customized sizes

MDF SPECIFICATIONS

		11¼ 15¼ 23¼
Width	-	11¼ 15¼ 23¼
Internal Bond	12 mm - 15 mm	17 - 30 mm
Density	31 lbs.	31 lbs.
Thickness	87 psi	87 psi
Molding Rupture	4,000 psi	3,700 psi
Molding Elasticity	280,000 psi	260,000 psi
Water Absorption (24hrs.)	40%	40%
Thickness Swell (24hrs.)	10%	8%
Moisture Content	8%	8%
Face	168 lbs.	168 lbs.
Edge	135 lbs.	135 lbs.

MDP SPECIFICATIONS

PROPERTIES	UNIT	THICKNESS					
		9	12	15	18	24	32
Density	[Kg/m ³]	660 ± 20	640 ± 20	620 ± 20	610 ± 20	590 ± 20	570 ± 20
Flexión	[N/mm ²]	16 ± 1,5	16 ± 1,5	15 ± 1,5	15 ± 1,5	15 ± 1,5	13 ± 1,5
Perpendicular Traction	[N/mm ²]	0,50 ± 0, 12	0,50 ± 0,12	0,50 ± 0,15	0,50 ± 0,15	0,45 ± 0,15	0,40 ± 0,15
Perpendicular Traction	[N]	-	-	Mín. 900	Mín. 900	Mín. 900	Mín. 900
Parallel Screw	[N]	-	-	Mín. 700	Mín. 700	Mín. 700	Mín. 700
Swelling 24hrs	[%]	Máx. 25	Máx. 25	Máx. 25	Máx. 25	Máx. 25	Máx. 25
Humidity	[%]	8 ± 3	8 ± 3	8 ± 3	8 ± 3	8 ± 3	8 ± 3
Toluene Test	mm	Mín. 160	Mín. 160	Mín. 160	Mín. 160	Mín. 160	Mín. 160

*Consult for formats and thicknesses.

Masisa reserves the right to modify the properties of this product without prior notice.

Information Update to august 2022.